



GLASS, POLYCARBONATE &

POLYURETHANE

TESTED TO
5 ROUNDS
OF .308



SPECIFICATIONS

21.4 LBS

BALLISTIC RATING: MEETS OR EXCEEDS THE FOLLOWING

· UL752 LEVEL 8 BALLISTIC STANDARD

TECHNICAL DATA

THIS BALLISTIC GLAZING WILL WITHSTAND 5 ROUNDS OF .308 (7.62X51) IN A ONE SQUARE FOOT SAMPLE, UTILIZING A LEAD CORE PROJECTILE WITH A MASS OF 145 GRAIN (11.67 GRAM) TRAVELING AT 2780 FEET / SECOND (847.9 METERS /SECOND) WITH EACH ROUND DELIVERING AN IMPACT OF 3379 JOULES OF ENERGY AND A MOMENTUM OF 7.97 KG M/S. THIS BALLISTIC GLAZING MAY ALSO PROVIDE UP TO 30 MINUTES OF FORCED ENTRY PROTECTION.

- NOMINAL THICKNESS: 2 1/16"; 2.063"; 52.4002MM
- WEIGHT PER SOUARE FOOT: 21.4 LBS: 9.7156KG

FRAMING OPTIONS

· STEEL

SIZING INFORMATION

UP TO 70" X 128"

8-1820-LS

TESTING CERTIFICATIONS

BGAS0418231